


LV650 Sealer – 2PK



6 LV650 Sealer 2PK
1 LV650 Hardener




Use Sikkens Measuring Stick Number
23



Spray gun set-up (Gravity Feed):	Fluid Delivery:
1.2 – 1.4 mm	10 - 14 oz / min
Max 10 psi	Check gun manufacturer specification



Apply one (1) single flowing coat



Wet on wet with Topcoat
20 minutes at 70°F (21°C)



Before Topcoat	70°F (21°C)	140°F (60°C)
Dry to Sand	20 min	1 hour
	8 hrs	



Recoat with LV650 Basecoat, LV650 Topcoat, ABP RV – Q10RV or Q35RV Binder with BT300 Hardener



Use suitable respiratory protection
AkzoNobel recommends the use of a fresh air supply respirator



Autocoat BT